

Document made available under the Patent Cooperation Treaty (PCT)

International application number: PCT/US05/004477

International filing date: 14 February 2005 (14.02.2005)

Document type: Certified copy of priority document

Document details: Country/Office: GB
Number: 0407433.2
Filing date: 01 April 2004 (01.04.2004)

Date of receipt at the International Bureau: 11 March 2005 (11.03.2005)

Remark: Priority document submitted or transmitted to the International Bureau in compliance with Rule 17.1(a) or (b)



World Intellectual Property Organization (WIPO) - Geneva, Switzerland
Organisation Mondiale de la Propriété Intellectuelle (OMPI) - Genève, Suisse



PCT/US 05 / 04 477



INVESTOR IN PEOPLE


The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.




Signed

Andrew Gersey

Dated

31 January 2005



01APR04 ERS5744-1 002914
P01/7700 0.00-0407433.2 ACCOUNT CHA

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
South Wales
NP9 1RH

1. Your reference
DC 10 005

21 APR 2004

2. Patent application number
(The Patent Office will fill in this part)

0407433.2

3. Full name, address and postcode of the or of each applicant (underline all surnames)

DOW CORNING CORPORATION
Midland
Michigan 48611
USA

Patents ADP number (if you know it)

8506040002

If the applicant is a corporate body, give the country/state of its incorporation

USA/Michigan

4. Title of the invention

SUBSTITUTED AMINOSILOXANES AND POLYMERIC PRODUCTS

5. Name of your agent (if you have one)

P V Davies

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

DOW CORNING LIMITED
Intellectual Property Department
Cardiff Road
Barry
CF63 2YL

Patents ADP number (if you know it)

414037001

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

Yes

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description

19

Claim(s)

4

Abstract

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*)

Request for preliminary examination and search (*Patents Form 9/77*)

1

Request for substantive examination (*Patents Form 10/77*)

Any other documents
(*please specify*)

1 fee sheet

11.

I/We request the grant of a patent on the basis of this application.

Signature

P V Davies

Date

P V Davies

31 March 2004

12. Name and daytime telephone number of person to contact in the United Kingdom

P V Davies 01446 723505

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

SUBSTITUTED AMINOSILOXANES AND POLYMERIC PRODUCTS

[0001] This invention relates to substituted aminosiloxanes and to methods of preparing the substituted aminosiloxanes. It also relates to polymeric products derived from the substituted aminosiloxanes and to their preparation. The polymeric products are suitable for application to substrates such as textiles, particularly fabrics, to impart oil repellent properties (oleophobicity) to the textile, and to the preparation of the polymeric products.

[0002] Fluorocarbon polymers are extensively used in the textile industry to impart oleophobicity/oil repellency to a fabric. For example, US-A-5247008 describes finishing agents for textiles, leather, paper and mineral substrates which are aqueous dispersions of a copolymer of a perfluoroalkyl acrylate or methacrylate, an alkyl acrylate or methacrylate and an aminoalkyl acrylate or methacrylate.

[0003] US-A-5068295 describes a water and oil repellent comprising a copolymer of a perfluoroalkyl acrylate or methacrylate, a polyorganosiloxane containing a vinyl group and a vinyl monomer containing an isocyanate or blocked isocyanate group.

[0004] US-A-6582620 and US-A- 5883185 describe a treating composition for textiles to render them water and oil repellent obtained by cohydrolysis and condensation of (A) a fluorinated alkyl-bearing alkoxy silane, (B) an amino-bearing alkoxy silane, and (C) an alkoxy silyl-bearing polyorganosiloxane.

[0005] US-A-5536304 describes application of a blend of a succinic anhydride-terminated polydimethylsiloxane and a poly(fluoroalkyl methacrylate) to cotton to give a fabric with oil repellency.

[0006] US-A-6472019 describes treating a textile with a water- and oil-repellent agent comprising a fluorine-containing polymer and a sulphated fatty acid compound.

[0007] One of the major disadvantages of topical finishes prepared with fluorocarbon polymers is that they impart a harsh feel to the fabric surface. There is a need for textile

treatment agents which impart oleophobicity and oil repellency to fabrics without imparting a harsh feel to the fabric surface, and preferably whilst at the same time imparting an improvement in feel compared to untreated fabric.

5 [0008] According to one aspect of the invention, at least some of the amino groups of an aminosiloxane are substituted by an ethylenically unsaturated group bonded by an organic moiety to the amino group, the organic moiety including an ester linkage. By an ethylenically unsaturated group we mean a group of the formula $\text{CH}_2=\text{C}(\text{J})-$, where J is a hydrogen atom or a hydrocarbyl group (which can be substituted).

10

[0009] According to another aspect of the invention, a process for the preparation of a substituted aminosiloxane is characterised in that a polydiorganosiloxane containing aminoalkyl groups of the formula $\text{R}-(\text{NH}-\text{A}')_q-\text{NH}-\text{A}-$ attached to silicon, wherein A and A' are each independently a linear or branched alkylene group having 1 to 6 carbon atoms; $q = 0-15$ 4; and R is hydrogen or an alkyl or hydroxyalkyl group having 1 to 4 carbon atoms, is reacted with a compound containing two ethylenically unsaturated groups

[0010] The invention also includes the carbon-to-carbon addition polymerisation of such a substituted aminosiloxane, optionally with one or more ethylenically unsaturated comonomer, and the polymeric product produced by this polymerisation.

20


[0011] According to a further aspect of the invention a polymeric product having oil resistant properties comprises an addition copolymer of

- 25
- i. an aminosiloxane containing amino groups substituted by an olefinically unsaturated group,
 - ii. a fluoro-substituted alkyl ester of an olefinically unsaturated carboxylic acid and optionally
 - iii. one or more ethylenically unsaturated comonomers.

30

[0012] The invention also includes a textile treatment composition comprising such a polymeric product, and a process for rendering fabric, leather or paper oleophobic in which the polymeric product is applied to the fabric, leather or paper.

5 [0013] In the polydiorganosiloxane containing aminoalkyl groups attached to silicon, the aminoalkyl groups can be terminal groups to the polydiorganosiloxane and/or pendant to the polydiorganosiloxane chain. The amino groups are preferably secondary or primary amino groups and the aminoalkyl groups are preferably of the formula



10 wherein A and A' are each independently a linear or branched alkylene group having 1 to 6 carbon atoms; q = 0-4; and R is hydrogen, an alkyl or hydroxyalkyl group having 1 to 4 carbon atoms, or an alkoxyalkyl or carboxyalkyl group having 1 to 4 carbon atoms in the alkyl moiety. If R is a carboxyalkyl group, it is preferably esterified. Most preferably q = 0 or 1; and A and A' (if present) each contain 2 to 4 carbon atoms.

15


[0014] The groups attached to silicon other than aminoalkyl groups are generally optionally substituted alkyl, aryl or aralkyl groups and are preferably alkyl groups having 1 to 4 carbon atoms, most preferably methyl groups. The polysiloxane is preferably linear but can be branched, for example it can contain branching units such as $CH_3SiO_{3/2}$ units, but such

20 branching units preferably form no more than 5 mole% of the polysiloxane.

[0015] The polydiorganosiloxane containing aminoalkyl groups attached to silicon used in the invention can for example be of the formula



25 where A, A', R and q are defined as above and x is for example 4-1000, or may have the formula



30


where A, A', R and q are defined as above; Y is an optionally substituted alkyl or aryl group; Z and Z', which can be the same or different, are each an optionally substituted alkyl, aryl or aralkyl group; X is hydrogen or an aliphatic group, preferably an alkyl group having 1 to 30, particularly 6 to 20, carbon atoms, or a triorganosilyl group such as trimethylsilyl; m is for example 4-1000; and n is for example 1-1000, preferably 2-100. The preparation of such amino-functional polysiloxanes is described in WO-A-03/16380.

[0016] The aminosiloxane in which at least some of the amino groups are substituted by an ethylenically unsaturated group can be prepared by reacting the said polydiorganosiloxane containing aminoalkyl groups attached to silicon with an ester compound containing two ethylenically unsaturated groups. Preferably the ester compound contains two acrylate or methacrylate ester groups. The amino groups of the polydiorganosiloxane containing aminoalkyl groups react with one of the ethylenically unsaturated groups of the ester compound by Michael-type addition



[0017] The amino groups of the polydiorganosiloxane containing aminoalkyl groups that is reacted with the compound containing two ethylenically unsaturated groups are preferably secondary amine groups. Primary amino groups react more readily with ethylenically unsaturated groups in Michael-type addition than secondary amine groups do, but the product is a secondary amine which can take part in further Michael-type addition. This can lead to crosslinked and potentially intractable materials. The secondary amine groups can be formed during preparation of the polydiorganosiloxane containing aminoalkyl groups or can be formed from a polydiorganosiloxane containing primary amino groups by a Michael-type addition reaction with a compound containing a single ethylenically unsaturated group, for example an acrylate or methacrylate ester group.


[0018] The polydiorganosiloxane containing primary amino groups can for example contain aminoalkyl groups of the formula



and can be of the formula



or











where A, A', q, Y, Z and Z', x, m and n are defined as above. Examples of preferred aminoalkyl groups containing primary amino groups include $-(CH_2)_3NH_2$, $-(CH_2)_4NH_2$, $-(CH_2)_3NH(CH_2)_2NH_2$, $-CH_2CH(CH_3)CH_2NH(CH_2)_2NH_2$, -


15 $(CH_2)_3NHCH_2CH_2NH(CH_2)_2NH_2$,
 $-CH_2CH(CH_3)CH_2NH(CH_2)_3NH_2$,
 $-(CH_2)_3NH(CH_2)_4NH_2$ and $-(CH_2)_3O(CH_2)_2NH_2$.

[0019] The aminosiloxane can be a modified aminosiloxane. For example, prior to
 20 reaction of the aminosiloxane with a molecule containing two ethylenically unsaturated groups it can be reacted with a compound reactive with amino groups such as a lactone, epoxide, isocyanate or anhydride. Lactones react with amino groups to form an amidic ester linkage. Epoxides react with amino groups $-NHR$ to form a $-N(R)-CH_2-CHOH-$ linkage. Isocyanates react with amino groups to form a urea linkage. Anhydride groups react with
 25 amino groups to form an amide linkage. The modifying reaction is preferably carried out with a molar ratio of ethylenically unsaturated groups to primary amino groups of less than 1:1, for example 0.1:1 to 0.9:1, particularly 0.4:1 to 0.8:1, so that many but not all of the primary amino groups are modified. The remaining amino groups are then reacted with diacrylate to yield the acrylate functional siloxane. This method of first reacting most of the
 30 available NH bonds helps to control the amount of acrylate functionality incorporated into the aminopolysiloxane.


[0020] The compound containing a single ethylenically unsaturated group which is reacted with the polydiorganosiloxane containing primary amino groups is preferably an acrylate or methacrylate ester, although alternative compounds such as acrylonitrile, vinyl chloride or styrene can be used. The acrylate or methacrylate ester is preferably of the

- 5 formula $\text{CH}_2=\text{CR}''\text{-COO-R}'$, where R'' is hydrogen or methyl and R' is an alkyl or substituted alkyl group having 1 to 20 carbon atoms. Acrylate esters are preferred as they more readily undergo Michael-type addition. Examples of alkyl esters are methyl, ethyl, butyl, hexyl, 2-ethylhexyl, octyl and lauryl esters. Examples of substituted alkyl esters are fluoroalkyl esters, particularly when preparing polymeric products suitable for application to substrates to impart
- 10 oil repellent properties. The fluoroalkyl acrylate or methacrylate ester can for example be of the formula $\text{CH}_2=\text{C(R}'')\text{COO-D-Rf}$ or $\text{CH}_2=\text{C(R}'')\text{COO-Rf}$, where Rf is a branched or linear fluoroalkyl group having 3 to 21 carbon atoms, for example a perfluoroalkyl group, R'' is H or methyl, and D is a divalent organic group. D may for example be a linear or branched alkylene group having 1 to 20 carbon atoms, for example a group of the formula $-(\text{CH}_2)_x-$
- 15 where x is 1 to 10, a group of the formula $-\text{SO}_2\text{N(R}^1\text{)R}^2-$ or of the formula $-\text{CON(R}^1\text{)R}^2-$, where R^1 is an alkyl group having 1 to 10 carbon atoms and R^2 is a linear or branched alkylene group having 1 to 10 carbon atoms, or a group of the formula $-\text{CH}_2\text{CH(OR}^3\text{)CH}_2-$ where R^3 represents a hydrogen atom or an acyl group having 1 to 10 carbon atoms such as formyl or acetyl, or a group of the formula $-\text{Ar-CH}_2-$ where Ar is an arylene group optionally
- 20 having a substituent. Specific examples of suitable fluoroalkyl acrylate esters are





(where Ph represents 1,4-phenylene)



5 [0021] The Michael-type addition reaction between the polydiorganosiloxane containing primary amino groups and the compound containing a single ethylenically unsaturated group is preferably carried out with a molar ratio of ethylenically unsaturated groups to primary amino groups of 1:1 or less, for example 0.4:1 to 0.9:1, so that many but not all of the primary amino groups are converted to secondary amino groups. The reaction
10 can be carried out at any temperature between 20 and 200°C which is below the boiling point of the reagents, preferably at 50-120°C. The reaction can be carried out in bulk if the reagents are liquid but are preferably carried out in polar organic solvent solution. Suitable polar organic solvents include aromatic hydrocarbons such as xylene or toluene, alcohols such as butan-1-ol, ether alcohols such as butoxyethanol, esters such as butyl acetate and/or ketones
15 such as methyl isobutyl ketone.

[0022] The polydiorganosiloxane containing aminoalkyl groups, preferably secondary amine groups, is reacted with the compound containing two ethylenically unsaturated groups in a Michael-type addition reaction which is preferably carried in polar organic solvent
20 solution using the solvents and reaction temperatures described above. If the polydiorganosiloxane containing secondary amine groups is prepared by reaction between a polydiorganosiloxane containing primary amino groups and a compound containing a single ethylenically unsaturated group, the subsequent reaction with the compound containing two ethylenically unsaturated groups can be carried out in the same vessel without separation of
25 the intermediate product.

[0023] The ethylenically unsaturated groups of the compound containing two such groups are preferably acrylate ester groups but can alternatively be methacrylate ester groups. The compound can for example have the formula $\text{CH}_2=\text{CHR}''\text{-COO-X-OOC-CR}''=\text{CH}_2$,
30 where each R'' independently represents H or methyl and X represents a divalent organic linkage. Preferably X represents an alkylene group having 1 to 20 carbon atoms. The compound containing two ethylenically unsaturated groups can for example be hexane-1,6-

diol diacrylate, butane-1,4-diol diacrylate, propylene glycol diacrylate or ethylene glycol diacrylate. It undergoes a Michael-type addition reaction with the polydiorganosiloxane containing aminoalkyl groups to form substituted amine groups containing ethylenically unsaturated groups of the formula

5



[0024] The compound containing two ethylenically unsaturated groups is preferably used in molar excess compared to amine groups of the aminosiloxane to avoid crosslinking of the aminosiloxane. The compound containing two ethylenically unsaturated groups can for example be used in 5 to 50% molar excess if it is desired to use the reaction product without purification, or can be used at 20 to 100% or even greater molar excess with removal of unreacted bis-ethylenically unsaturated compound.

15 [0025] The aminosiloxane substituted by an ethylenically unsaturated group can be used to produce a polymeric product by carbon-to-carbon addition polymerisation, optionally with one or more ethylenically unsaturated comonomer. In particular the aminosiloxane can be copolymerised with a fluorocarbon monomer to form a treatment agent for fibrous products such as textiles, leather or paper which impart oleophobicity and oil repellency to the fibrous products without imparting a harsh feel. The aminosiloxane (I) can for example be copolymerised with (II) a fluoro-substituted alkyl ester of an olefinically unsaturated carboxylic acid and optionally (III) one or more ethylenically unsaturated comonomers.

[0026] The fluoro-substituted alkyl ester monomer (II) is preferably an acrylate or methacrylate ester of the formula $\text{CH}_2=\text{C}(\text{R}'')\text{COO}-\text{D}-\text{Rf}$ or $\text{CH}_2=\text{C}(\text{R}'')\text{COO}-\text{Rf}$, where Rf, R'' and D are defined as above. Specific examples of the fluoro-substituted alkyl ester monomer (B1) are

$\text{CF}_3(\text{CF}_2)_7(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$
 $\text{CF}_3(\text{CF}_2)_7(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 30 $\text{CF}_3(\text{CF}_2)_7(\text{CH}_2)_{10}\text{OCOCH}=\text{CH}_2$
 $\text{CF}_3(\text{CF}_2)_7(\text{CH}_2)_{10}\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 $\text{CF}_3(\text{CF}_2)_6\text{CH}_2\text{OCOCH}=\text{CH}_2$

- $\text{CF}_3(\text{CF}_2)_8\text{CH}_2\text{OCOCH}=\text{CH}_2$
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_6(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_8(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_{10}(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$
 5 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_6(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_8(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_{10}(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 $\text{CF}_3(\text{CF}_2)_9(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$
 $\text{CF}_3(\text{CF}_2)_9(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 10 $\text{CF}_3(\text{CF}_2)_{11}(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$
 $\text{CF}_3(\text{CF}_2)_{11}(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 $\text{CF}_3(\text{CF}_2)_7\text{SO}_2\text{N}(\text{CH}_3)(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$
 $\text{CF}_3(\text{CF}_2)_7\text{SO}_2\text{N}(\text{C}_2\text{H}_5)(\text{CH}_2)_2\text{OCOCH}=\text{CH}_2$
 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_8\text{CH}_2\text{CH}(\text{OCOCH}_3)\text{CH}_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 15 $(\text{CF}_3)_2\text{CF}(\text{CF}_2)_6\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{OCOCH}=\text{CH}_2$
 $\text{C}_8\text{F}_{17}\text{-O-Ph-CH}_2\text{OCOCH}=\text{CH}_2$ (where Ph represents 1,4-phenylene)
 $\text{C}_5\text{F}_{11}\text{-O-Ph-CH}_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 $\text{C}_8\text{F}_{17}\text{-O-Ph-COOCH}_2\text{CH}(\text{OH})\text{CH}_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$
 $(\text{CF}_3)_2\text{CFOCOC}(\text{CH}_3)=\text{CH}_2$
 20 $(\text{CF}_3)_2\text{CF}(\text{CH}_2)_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$

- Esters with a relatively long chain perfluoroalkyl moiety such as heptadecafluorodecyl may be preferred as because they have been widely used in the past to give good oil repellency, or esters with a relatively short chain perfluoroalkyl moiety such as nonafluorohexyl may be preferred as being less persistent in the environment. The fluoro-substituted alkyl ester monomer (B1) can if desired be a perfluoroalkyl acrylate or methacrylate such as nonafluorohexyl methacrylate or acrylate.
- 25

- [0027] The aminosiloxane and the fluorocarbon monomer can optionally be copolymerised with one or more olefinically unsaturated comonomers.(III). Examples of such olefinically unsaturated comonomers include alkyl acrylate or methacrylate esters having 1 to 30 carbon atoms in the alkyl group such as butyl acrylate, ethyl acrylate, methyl acrylate,
- 30

methyl methacrylate or butyl methacrylate. The alkyl acrylate or methacrylate can be used to adjust the glass transition temperature (T_g) of the copolymer (B); for example an acrylate having a long chain alkyl group of 4-20, particularly 8-20 carbon atoms such as stearyl acrylate or methacrylate, octyl acrylate, 2-ethylhexyl acrylate or dodecylacrylate or methacrylate can be used to form a softer polymer of lower T_g. Copolymers with an alkyl acrylate or methacrylate monomer may improve various properties such as water- and oil-repellency and soil releasability, cleaning durability, washing durability and abrasion resistance of such repellency and releasability, solubility in solvent, hardness and feel (handle). Other acrylate or methacrylate comonomers (B3) which can be used are polyethylene glycol acrylate or methacrylate, polypropylene glycol acrylate or methacrylate, methoxypolyethylene glycol acrylate or methacrylate and methoxypolypropylene glycol acrylate or methacrylate, Other olefinically unsaturated comonomers (B3) which can be used are vinyl chloride, vinylidene chloride, styrene, acrylonitrile, methacrylonitrile, ethylene, a vinyl alkyl ether, isoprene or a vinyl ester such as vinyl acetate or vinyl propionate. An olefinically unsaturated comonomer (B3) can be used which contains a functional group that, although not reactive with amine groups, may be reactive with other functional groups to give properties such as increased substantivity on textiles and other substrates. Examples of such functional groups are hydroxyl, amino and amide, and examples of olefinically unsaturated comonomers (B3) containing them are acrylamide, methacrylamide, N-methylolacrylamide, hydroxyethyl methacrylate, hydroxyethyl acrylate, 3-chloro-2-hydroxypropyl acrylate or methacrylate, N, N-dimethylaminoethyl acrylate or methacrylate and diethylaminoethyl acrylate or methacrylate.

[0028] The polymeric product can be prepared by free radical polymerisation of the monomers, preferably in solution, for example in a polar organic solvent such as one or more alcohol, ketone or ester solvents selected from butanol, t-butanol, isopropanol, butoxyethanol, methyl isobutyl ketone, methyl ethyl ketone, butyl acetate or ethyl acetate and/or an aromatic hydrocarbon such as xylene, toluene or trimethylbenzene a blend of one or more of these. The initiator for free radical polymerisation is preferably an azo compound such as azobisisobutyronitrile or azoisovaleronitrile (AIVN) but can be a peroxide such as benzoyl peroxide. The polymerisation temperature can for example be in the range 50-120°C. The free radical polymerisation can if desired be carried out without separation of the

aminosiloxane substituted by an ethylenically unsaturated group, for example by adding the fluorocarbon monomer and optionally one or more ethylenically unsaturated comonomers, and the initiator for free radical polymerisation, to the vessel in which the aminosiloxane substituted by an ethylenically unsaturated group was prepared.

5

[0029] Alternatively the polymeric product can be obtained using the technique of emulsion polymerisation, where all the components are polymerised in the presence of water, surfactants and polymerisation initiator.

10

[0030] The polymeric product can contain various ratios of the aminosiloxane, the fluoro-substituted monomer and the comonomer(s). The copolymer can for example contain 20 to 70% by weight of the aminosiloxane (I), 15 to 60% by weight of the fluoro-substituted alkyl ester (II) and 0 to 65% comonomer(s) (III). A polymeric product having a high proportion of aminosiloxane may be preferred for greater substantivity to fibrous substrates or softness of handle of the treated material. A polymeric product having a high proportion of fluoromonomer may be preferred for maximum hydrophobicity and oleophobicity.

15

[0031] The polymeric addition polymerisation product is generally obtained as a solution. It can be isolated by evaporation of the solvent. For application as an oil repellent, the polymeric product is generally required in liquid form and the solution obtained by reaction can often be diluted to a solution suitable for application to textiles. Alternatively the polymeric product can be dissolved in a different solvent for application to textiles, for example in a polar organic solvent of higher boiling point. The polymeric product can alternatively be emulsified by mixing with water and an emulsifying agent, such as a cationic surfactant and/or a nonionic or anionic surfactant. The polymeric product can be isolated before emulsification or the polymerisation product solution can be emulsified, optionally with removal of solvent. If the polymeric product is obtained by emulsion polymerisation, the emulsion is generally used, diluted as required, without isolating the polymeric product.

25

30

[0032] The solution or emulsion of polymeric product can be applied to fibrous substrates such as textiles by any of the methods known for treatment of textiles with liquids. The concentration of the polymeric product in the solution applied to the textile can for

example be 0.5 to 20% by weight, preferably 1 to 5%. When the textile is a fabric, the fabric can be immersed in the solution or can be padded or sprayed with the solution. The treated textile is dried and is preferably heated, for example at 100-200°C, to develop the oil repellency.

5

[0033] The textile which is treated is preferably a fabric, including woven, knitted and nonwoven fabrics, fabrics in garment form and carpet, but can be a fibre or yarn or intermediate textile product such as a sliver or roving. The textile material can be a natural fibre such as cotton or wool, a manmade fibre such as viscose rayon or lyocell or a synthetic fibre such as polyester, polyamide or acrylic fibre, or can be a mixture of fibres such as a mixture of natural and synthetic fibres. The polymeric product of the invention is particularly effective in rendering cellulosic fibres such as cotton or rayon oleophobic and oil repellent. The process of the invention generally also renders the textile hydrophobic and water repellent. Fabric treatment with the polymeric product of the invention imparts oil repellency to fabrics whilst at the same time imparting an improvement in feel compared to untreated fabric and also imparting an improvement in feel compared to fabric treated with known fluoropolymer textile treatment agents.

10
15

[0034] The fibrous substrate can alternatively be leather. The polymeric product can be applied to leather from aqueous solution or emulsion at various stages of leather processing, for example during leather wet end processing or during leather finishing, to render the leather hydrophobic and oleophobic.

20

[0035] The fibrous substrate can alternatively be paper. The polymeric product can be applied to preformed paper or at various stages of papermaking, for example during drying of the paper.

25

[0036] The invention is illustrated by the following Examples, in which percentages are by weight.

30

Example 1:

[0037] An aminopropyl end blocked polydimethylsiloxane (degree of polymerisation (dp) 250, 30.4g), hexanediol diacrylate (1.22g), xylene (50.3g) and butan-1-ol (50.6g) were charged to a reaction vessel and heated to 90°C for twenty minutes under nitrogen. The molar ratio of hexanediol diacrylate to amino groups in the polysiloxane was 1.68:1. The reaction product, which was not isolated from solution, was polydimethyl siloxane endblocked with $\text{Si}(\text{CH}_3)_2\text{CH}_2\text{CH}_2\text{CH}_2\text{-NH-CH}_2\text{CH}_2\text{COO}(\text{CH}_2)_6\text{OOCCH=CH}_2$ groups.

10

[0038] After twenty minutes hydroxyethylmethacrylate (16.6g), dodecanethiol (1.05g), $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_2\text{C}_8\text{F}_{17}$ fluoromonomer FM (26.5g) and 1,1'-azo-bis-cyclohexanecarbonitrile (0.45g) were then charged to the reaction vessel and the temperature maintained at 90°C under nitrogen for a further six hours. After six hours the reaction was cooled to yield a solution of a soft oil and water repellent polymer.

15


[0039] The resulting solution was then diluted with 2-butanone to yield a solution containing 2% w/w polymer. The resulting solution was then applied to a range of fabrics. The solution was applied to the fabric (6cmx6cm piece) to give 100% wet pick up. The fabrics were then air dried for 24 hours and then heat cured at 150°C for three minutes.

20

[0040] The oil and water repellency and hand of the fabrics were evaluated and the results are shown in Tables 1 to 4 below.

Example 2:

[0041] An amino-functional siloxane (40.5g) of the formula



(R is a mixture of linear and branched hydrocarbons C13)

[II]

stearyl acrylate (5.2g), xylene (50.3g) and butan-1-ol (50.7g) were charged to a reaction vessel and heated to 90°C for fifteen minutes under nitrogen. The molar ratio of stearyl acrylate to amino groups in the polysiloxane was 0.8:1. The reaction product, which was not isolated, contained -NH-CH₂CH₂COOC₁₈H₃₇ groups.

[0042] To the reaction vessel was then added hexanediol diacrylate (1.53g) and the reaction held at 90°C for a further fifteen minutes under nitrogen. The reaction product, which was not isolated from solution, contained



!


-NH-CH₂CH₂COO(CH₂)₆OOCCH=CH₂ groups.

[0043] Fluoromonomer FM (30.3g), hydroxyethylmethacrylate (16.5g), dodecanethiol (1.06g), 2-butanone (30g) and, 1,1'-azo-bis-cyclohexanecarbonitrile (0.45g) were then added to the reaction vessel and the reaction temperature maintained at 90°C for seven hours to yield a solution of a soft water and oil repellent polymer.

[0044] The resulting solution was then diluted with 2-butanone to yield a solution containing 2% w/w polymer and was applied to fabrics and tested as described in Example 1.

Example 3

[0045] An amino-functional siloxane [III] (40.2g 0.4 % nitrogen and $x+y \sim 270$) of the formula



(R is a mixture of linear and branched hydrocarbons C13)

[III]

stearyl acrylate (5.18g), xylene (51.6g) and butan-1-ol (53.5g) were charged to a reaction vessel and heated to 90°C for fifteen minutes under nitrogen. The molar ratio of stearyl acrylate to N-H amino groups in the polysiloxane was 0.73:1. The reaction product, which was not isolated, contained -NH-CH₂CH₂COOC₁₈H₃₇ groups.

[0046] Fluoromonomer CH₂=CHCOO(CH₂)₂C₈F₁₇ FA (30.8g), hydroxyethylmethacrylate (16.9g), dodecanethiol (1.06g), 2-butanone (30g) and, 1,1'-azo-bis-cyclohexanecarbonitrile (0.45g) were then added to the reaction vessel and the reaction temperature maintained at 90°C for seven hours to yield a solution of a soft water and oil repellent polymer.

[0047] The resulting solution was then diluted with 2-butanone to yield a solution containing 2% w/w polymer and was applied to fabrics and tested as described in Example 1.

Comparative Example

[0048] Fluoromonomer CH₂=CHCOO(CH₂)₂C₈F₁₇ FA (30.2), hydroxyethylmethacrylate (16.1), dodecanethiol (1.05), 2-butanone (32.8g) and, 1,1'-azo-bis-cyclohexanecarbonitrile (0.45g) were then added to the reaction vessel and the reaction temperature maintained at 90°C for seven hours to yield a reference oil and water repellent fluorocarbon polymer.

[0049] In the tests reported in Tables 1 to 4, this fluorocarbon polymer was used alone and in blends with each of the aminosiloxanes (I), (II) and (III).

Test Methods

5

[0050] The oil repellency of the treated fabrics was evaluated using AATCC test method 118-1997.

10

[0051] The water repellency of the treated fabrics was evaluated using the spray test method, AATCC 22-1996. ...

[0052] Water repellency was also measured by the IPA/water test, in which various solutions water/isopropanol having ratios by volume comprised from 100/0 to 0/100 as reported in the table below.

15

Solution H ₂ O/IPA (vol/vol)	Water repellency Index
100/0	0
90/10	1
80/20	2
70/30	3
60/40	4
50/50	5
40/60	6
30/70	7
20/80	8
10/90	9
0/100	10

[0053] Four drops with a diameter of approximately 3mm of the isopropanol/water solution are deposited on a sample of treated fabric. The behaviour of the four drops is observed for a time of 30 seconds. If three out of the four drops show no absorption or

darkening of the fabric then one moves to the next solution with a higher content of isopropanol. The water repellency index/rating relates to the last test solution that did not absorb into or darken the fabric surface.

- 5 [0054] The handle of the treated cotton fabrics was assessed on a scale of 1 to 10, where 1 = harsh, 10 = very soft

Table 1: Results for oil repellency

Sample	Cotton	Cotton/Polyester	Polyester	Nylon
Example 1	4	5	5	5
Example 2	5	6	6	6
Example 3	6	7	6	6
Control	6	6	6	6
Control + 0.3% w/w [I]	2	3	2	2
Control + 0.3% w/w [II]	1	2	2	1
Control + 0.3% w/w [III]	1	1	2	1

10

- [0055] Table 1 shows that the oil repellency of fabrics treated with the fluorosilicone hybrid polymeric products of the invention is better than fabrics treated with the control fluorocarbon polymer blended with the aminosilicones used to prepare the hybrid polymeric products. The oil repellency of fabrics treated with the fluorosilicone hybrid polymeric products of Examples 2 and 3 is as good as fabrics treated with the control fluorocarbon polymer.
- 15

Table 2 : Results for water repellency spray test.

Sample	Cotton	Cotton/Polyester	Polyester	Nylon
Example 1	80	80	90	90
Example 2	90	90	90	80
Example 3	90	80	90	90
Control	80	80	90	90
Control + 0.3% w/w [I]	70	70	80	60
Control + 0.3% w/w [II]	70	80	70	80
Control + 0.3% w/w [III]	60	60	70	70

5 Table 3 : Results for IPA/water test

Sample	Cotton	Cotton/Polyester	Polyester	Nylon
Example 1	8	8	8	8
Example 2	9	10	9	10
Example 3	10	10	10	9
Control	9	8	8	8
Control + 0.3% w/w [I]	7	8	7	7
Control + 0.3% w/w [II]	8	8	7	8
Control + 0.3% w/w [III]	6	6	6	7

[0056] Tables 2 and 3 show that the water repellency of fabrics treated with the fluorosilicone hybrid polymeric products of the invention is better than fabrics treated with the control fluorocarbon polymer blended with the aminosilicones used to prepare the hybrid polymeric products, and as good as fabrics treated with the control fluorocarbon polymer.

Table 4 : Handle Evaluation

Sample	Handle
Example 1	6
Example 2	8
Example 3	10
Control	2
Control + 0.3% w/w [I]	6
Control + 0.3% w/w [II]	7
Control + 0.3% w/w [III]	9


[0057] Table 4 shows that the handle of fabrics treated with the fluorosilicone hybrid polymeric products of the invention is at least as soft as fabrics treated with the control fluorocarbon polymer blended with the aminosilicones used to prepare the hybrid polymeric products, and is very much softer than fabrics treated with the control fluorocarbon polymer alone.

CLAIMS

1. An aminosiloxane, characterised in that at least some of the amino groups of the aminosiloxane are substituted by an ethylenically unsaturated group bonded by an organic moiety to the amino group, the organic moiety including an ester linkage.
2. An aminosiloxane according to Claim 1, characterised in that the said amino groups are substituted by a group of the formula
$$-\text{CH}_2\text{CHR}''-\text{COO}-\text{X}-\text{OOC}-\text{CR}''=\text{CH}_2,$$
where each R'' independently represents H or methyl and X represents a divalent organic linkage.
3. An aminosiloxane according to Claim 2, characterised in that X represents an alkylene group having 1 to 20 carbon atoms.
4. An aminosiloxane according to any of Claims 1 to 3, characterised in that the aminosiloxane is also substituted by an organic moiety which has no ethylenic unsaturation.
5. An aminosiloxane according to Claim 4 characterised in that substantially all of the amino groups are present as tertiary amino groups.
6. An aminosiloxane according to any of Claims 1 to 4 characterised in that some of the amino groups of the aminosiloxane are unsubstituted aminoalkyl groups of the formula $\text{R}-(\text{NH}-\text{A}')_q-\text{NH}-\text{A}-$ attached to silicon, wherein A and A' are each independently a linear or branched alkylene group having 1 to 6 carbon atoms; $q = 0-4$; and R is hydrogen or an alkyl or hydroxyalkyl group having 1 to 4 carbon atoms.
7. An aminosiloxane according to any of Claims 1 to 6 which is an aminoalkyl-endblocked polydiorganosiloxane.

8. An aminosiloxane according to any of Claims 1 to 7 characterised in that the aminosiloxane also contains amino groups modified by reaction with a lactone, epoxide, isocyanate or anhydride.

9. A process for the preparation of a substituted aminosiloxane, characterised in that a polydiorganosiloxane containing aminoalkyl groups of the formula



wherein A and A' are each independently a linear or branched alkylene group having 1 to 6 carbon atoms; $q = 0-4$; and R is hydrogen or an alkyl or hydroxyalkyl group having 1 to 4 carbon atoms, is reacted with a compound containing two ethylenically unsaturated groups

10. A process according to Claim 9, characterised in that the ethylenically unsaturated groups are acrylate or methacrylate ester groups.
11. A process according to Claim 9 or Claim 10, characterised in that at least some of the amino groups in the polydiorganosiloxane containing aminoalkyl groups are primary amino groups, and the polydiorganosiloxane containing aminoalkyl groups is additionally reacted with a compound containing one ethylenically unsaturated group.
12. A process according to Claim 11, characterised in that the compound containing one ethylenically unsaturated group is an acrylate or methacrylate ester of the formula $CH_2=CR''-COO-R'$, where R' is an alkyl or substituted alkyl group having 1 to 20 carbon atoms.
13. A process according to Claim 12 characterised in that R' is a fluoroalkyl group.

14. A process according to any of Claims 11 to 13, characterised in that the polydiorganosiloxane containing aminoalkyl groups is reacted with the compound containing one ethylenically unsaturated group to form a Michael-type adduct, and the Michael-type adduct thus formed is reacted with the compound containing two ethylenically unsaturated groups
15. A substituted aminosiloxane produced by the process of any of Claims 9 to 14.
16. A polymeric product produced by carbon-to-carbon addition polymerisation of a substituted aminosiloxane as defined in any of Claims 1 to 8 or 15, optionally with one or more ethylenically unsaturated comonomer.
17. A polymeric product having oil resistant properties comprising an addition copolymer of
 - i. an aminosiloxane containing amino groups substituted by an ethylenically unsaturated group,
 - ii. a fluoro-substituted alkyl ester of an ethylenically unsaturated carboxylic acid and optionally
 - iii. one or more ethylenically unsaturated comonomers.
18. A polymeric product according to Claim 17, characterised in that the olefinically unsaturated group of the aminosiloxane is an acrylate or methacrylate ester group.
19. A polymeric product according to Claim 17 or Claim 18, characterised in that the aminosiloxane is a substituted aminosiloxane as defined in any of Claims 1 to 8 or 15.
20. A polymeric product according to any of Claims 17 to 19, characterised in that the fluoro-substituted alkyl ester monomer B1 is an acrylate or methacrylate ester of the formula

$$\text{CH}_2=\text{C}(\text{R}''')\text{COO-A-Rf}$$

where R_f is a fluoroalkyl group having 3 to 21 carbon atoms, R''' is H or methyl, and A is a divalent organic group.

21. A polymeric product according to any of Claims 17 to 20 characterised in that the copolymer contains a comonomer (III) which is a hydroxyalkyl acrylate or methacrylate having 1 to 20 carbon atoms in the hydroxyalkyl group.
22. A polymeric product according to any of Claims 17 to 21 characterised in that the copolymer contains 20 to 70% by weight of the aminosiloxane (I), 15 to 60% by weight of the fluoro-substituted alkyl ester (II) and 0 to 65% comonomer(s) (III).
23. A textile treatment composition comprising a polymeric product according to any of Claims 17 to 22.
24. A process for rendering fabric, leather or paper oleophobic characterised in that a polymeric product according to any of Claims 17 to 22 is applied to the fabric, leather or paper.

